

TECHNICAL DATA SHEET

SIPOLPRENE® 58210

DESCRIPTION

Sipolprene® 58210 is an ether ester thermoplastic elastomer (TPC-ET), developed and manufactured by Sipol, with a nominal hardness of Shore D 58, a medium modulus, and a rheological behaviour, which makes it suitable for injection molding and extrusion processing.

Sipolprene® 58210 comes in a natural color with a standard stabilisation package, fully in compliance with American FDA and European EU 10/2011 Food Contact Regulations.

Black color and/or UV stabilised and/or heat stabilised are all available in dry blend version on request.

TECHNICAL CHARACTERISTICS

Properties	Test methods		U.M.	Product
	ASTM	ISO		
Density	D 792	1183	g/cm ³	1.21
Hardness (instantaneous)	D 2240	868	Shore D	58
Strength at break	D 638	527	MPa	48
Elongation at break	D 638	527	%	500
Flexural Modulus	D 790	178	MPa	250
Tear Strength	D 1004	-	N/mm	207
Melting Temperature	D 3418	3146	°C	211
Vicat A/50	D 1525	306	°C	186
Abrasion resistance	DIN 53516		mm ³	18
Water absorption (23°C x 24 h immersion)	MI / 08		%	0.25
MFI 230°C 2.16 Kg	D 1238	1133	g/10 min	23
Izod impact resistance/notched (23°C)	D 256	-	J/m	No break

Last applicable edition of the Norm is valid as reference.

PACKAGING

Moisture proof bags of 25 kg net.
 Octabins of 500 kg net with PE film inside

Date issued: 20/09/2013
 Revision n°: 4

The data reported here fall within the normal range of properties, but they should not be considered to establish specification limits nor used alone as basis of design. Sipol assumes no obligations or liability for any advice furnished or for any results obtained with respect to this data sheet. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a license to operate under, or a recommendation to infringe, any existing patent. Our advice does not exempt the buyer from conducting his own checks and controls. The application, use and processing of Sipol's grades and the products manufactured by the buyers following our technical advice are entirely beyond our control and therefore completely under the buyer's responsibility.