

LATAMID 66 H2 G/50

Compound based on Polyamide 66 (PA 66).

Heat stabilised. Glass fibres. Product UL certified.

PHYSICAL PROPERTIES - Typical values	STANDARD	VALUE MEASURE UNITS
Density	ISO 1183	1.56 g/cm ³
Linear shrinkage at moulding - 2.0 mm thickness (at 60 MPa of cavity pressure)		
Longitudinal	ISO 294-4	0.30 ÷ 0.60 %
Transversal	ISO 294-4	0.65 ÷ 0.95 %
MECHANICAL PROPERTIES - Typical values		
IZOD impact strength (sample 63.5x12.7x3.2 mm)		
Notched, at +23°C	ASTM D 256-A	150 J/m
CHARPY impact strength (sample 80x10x4 mm)		
Unnotched, at +23°C	ISO 179-1eU	60 kJ/m ²
Notched, at +23°C	ISO 179-1eA	15 kJ/m ²
Tensile elongation (speed 5 mm/min)		
At break, 23°C	ISO 527 (1)	2.7 %
At break, 60°C	ISO 527 (1)	3 %
At break, 90°C	ISO 527 (1)	5 %
At break, 120°C	ISO 527 (1)	5 %
At break, 150°C	ISO 527 (1)	6 %
Tensile strength (speed 5 mm/min)		
At break, 23°C	ISO 527 (1)	220 MPa
At break, 60°C	ISO 527 (1)	185 MPa
At break, 90°C	ISO 527 (1)	150 MPa
At break, 120°C	ISO 527 (1)	130 MPa
At break, 150°C	ISO 527 (1)	100 MPa
Elastic modulus		
Tensile (speed 1 mm/min), at 23°C	ISO 527 (1)	16000 MPa
Tensile (speed 1 mm/min), at 60°C	ISO 527 (1)	12500 MPa
Tensile (speed 1 mm/min), at 90°C	ISO 527 (1)	9000 MPa
Tensile (speed 1 mm/min), at 120°C	ISO 527 (1)	7500 MPa
Tensile (speed 1 mm/min), at 150°C	ISO 527 (1)	5900 MPa

LATAMID 66 H2 G/50

Compound based on Polyamide 66 (PA 66).
Heat stabilised. Glass fibres. Product UL certified.

THERMAL PROPERTIES - Typical values		
	STANDARD	VALUE MEASURE UNITS
Coefficient of linear thermal expansion (CLTE)		
+30°C to +100°C (longitudinal)	ASTM D 696	7 µm/(m·°C)
VICAT - Softening point		
49 N (heating rate 50°C/h)	ISO 306	255 °C
HDT - Heat Deflection Temperature		
0.45 MN/m ²	ISO 75	260 °C
1.81 MN/m ²	ISO 75	255 °C
C.U.T. - Continuous Use Temperature (20,000h)		
	---	135 °C
FLAMMABILITY - Typical values		
Oxygen Index		
	ASTM D 2863	27 %
Flammability rating		
3.00 mm thickness	UL 94	HB rating
1.50 mm thickness	UL 94	HB rating
0.75 mm thickness	UL 94	HB rating

LATAMID 66 H2 G/50

Compound based on Polyamide 66 (PA 66).
Heat stabilised. Glass fibres. Product UL certified.

PREDRYING CONDITIONS

At least 3 hours at $90 \div 100^{\circ}\text{C}$

These are the suggested conditions to reduce the moisture content to adequate levels. Temperature and drying time are reduced when using vacuum ovens. A particularly wet material may need longer drying time.

ACTUAL MELT TEMPERATURE

$280 \div 310^{\circ}\text{C}$

The injection machine settings needed to obtain the suggested melt temperature will depend greatly on shot size and machine capacity, as well as other molding parameters such as: injection speed, screw RPM, back pressure, etc. On small machines, running short cycles, it is possible to use higher melt temperatures to improve plastification, fluidity and surface appearance, paying attention to any indication of material degradation.

MOULD TEMPERATURE

$80 \div 110^{\circ}\text{C}$

The mold temperature suggested above is the actual steel temperature. This can be significantly different from the tool settings, due to the cooling system efficiency and the accuracy of the temperature control on the tool.

INJECTION SPEED

Medium

The advisable injection speed greatly depends on cavity geometry and injection machine size. The use of high injection speed can improve the surface appearance, but it can also cause outgassing and burn marks due to overheating through shear stress.

REGRIND USAGE

The use of regrind is possible, but should be assessed on the basis of the project, moulding parameters, and type of grinding. The effect of using regrind on material properties must be evaluated by the customer on its specific project and process. High percentages of regrind can cause a reduction in viscosity and fibre length, reducing mechanical properties, reducing mechanical properties

HOT RUNNER MOULDS

Hot runner moulds can be used when a very tight temperature control is assured.

LATAMID 66 H2 G/50

Compound based on Polyamide 66 (PA 66).
Heat stabilised. Glass fibres. Product UL certified.

TO AVOID

Shut-off nozzles and internally heated hot runners have to be avoided. In order to prevent any material degradation, over-dimensioned machines should be avoided.

CONTACTS

LATI Industria Termoplastici S.p.A.

Via F. Baracca, 7 - I - 21040 VEDANO OLONA (VA)

Tel. +39-0332-409111 - Fax +39-0332-409260

[email: techserv@it.lati.com](mailto:techserv@it.lati.com)

<http://www.lati.com>

<http://lambda.lati.it>

NOTES

The products mentioned herein are not suitable for applications in contact with foodstuff or for potable water transportation, or for toy manufacturing. The products mentioned herein are not suitable for applications in the pharmaceutical, medical or dental sector.

Values shown are based on testing of injection moulded laboratory test specimens, conditioned according to the practice and represent data that fall within the standard range of properties for non-coloured material, if not otherwise specified. As they may be subject to variations, these values do not represent a sufficient basis for any part design and are not intended for use in establishing values for specification purposes. Properties of moulded parts can be influenced by a wide range of factors including, but not limited to, colorants, part design, processing conditions, post-treatment conditions, environmental conditions and usage of regrind during the moulding process. If data are explicitly indicated as provisional, range of properties has to be considered wider. This information and technical assistance are provided as a convenience for informational purposes only and are subject to change without notice. The customer shall always ensure that the latest release of technical information is at his own disposal. Lati S.p.A. extends no warranties or guarantee, including a warranty of merchantability of whatever use is made of the product, and make no representations as to the accuracy, suitability, reliability, completeness and sufficiency of the information provided, and assume no responsibility regarding the consequences of its use or for any printing errors. It is the customer's responsibility to inspect and test our products in order to determine to his own satisfaction whether they are suitable for his intended uses and applications or used in conjunction with third-party materials. This application-specific analysis shall at least include preliminary testing to determine the suitability for the customer's particular purpose from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us as the manner in which the customer use and the purpose to which utilise our products are beyond our control. Lati S.p.A. does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information. No one is authorised to make any warranties, issue any immunities or assume any liabilities on behalf of Lati S.p.A. except in a writing signed by a specifically authorised Lati S.p.A. executive. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at Lati's option, and in no event shall Lati S.p.A. be liable for special, consequential, incidental, punitive or exemplary damages. No information herein can be considered as a suggestion to use any product in conflict with intellectual property rights of third-parties. Lati S.p.A. disclaims any liability that may be claimed for infringement or alleged infringement of patents. For any other issues Lati S.p.A. Conditions of Sales apply.
Copyright © LATI S.p.A. 2008